Technical Datasheet

FLEX PU-40



Solvent-free, elastomeric adhesive and sealant

Description

FLEX PU-40 is a one-component, solventfree, elastomeric adhesive and sealant providing:

- Resistance to temperatures ranging from -40°C to +100°C.
- Excellent bonding to any kind of building material.
- High elasticity.
- Great resistance to aging and weather.
- Overpaintability after hardening, only with water-based paints.

Fields of application

FLEX PU-40 is suitable for sealing vertical and horizontal joints, on various materials such as concrete, aluminium, steel, wood, glass, natural and artificial stone, etc., both indoors and outdoors. Also suitable for bonding these materials.

In case of grouting on natural or artificial stones, such as marble and granite, please contact ISOMAT's Technical Support Department.

Technical data

Colors: white, grey, brown

Application temperature: from +5°C to +35°C

Film formation: $\approx 50-55 \text{ min}$ Curing speed: $\geq 3.5 \text{ mm/day}$

Hardness according to

SHORE A (DIN 53505): ≈ 45

Elastic modulus at 100% elongation

(DIN 52455): $1.0 \pm 0.1 \text{ N/mm}^2$

Elongation at break

(DIN 53504): $\geq 450\%$

Directions for use

1. Substrate preparation

Substrate must be dry and free of dust, loose particles, grease, etc. It is recommended that the joint is cleaned up by using a paintbrush or a wire brush and then air-blasted.

To avoid undesirable soiling at joint edges, a self-adhesive paper tape is applied alongside the edges and then removed immediately after sealing the joint (before a film is formed).

2. Application

The cartridge is inserted in the special gun and the nozzle is cut slantwise, so that it does not fit into the joint but barely touches and slides along the edges.

FLEX PU-40 is applied by moving the cartridge along the joint axis at a 45° angle. While still fresh, the sealant is leveled with a trowel.

Cleaning of tools:

Tools must be thoroughly cleaned with common solvents, while material is still fresh. If material has hardened, tools may only be mechanically cleaned.

Consumption

- Joint 10mm x 10mm:
 - 1 cartridge / 3 m of joint length.
- Joint 5mm x 5mm:
 - 1 cartridge / 12 m of joint length.

Packaging

- Cartridges of 310 ml.
- Sausages of 600 ml.

Shelf life – Storage

Shelf life is 12 months, in dry and frost-free conditions.



